

One side heat sealable, other side treated, white opaque BOPP film.

Properties

- · Good stiffness
- High gloss printing side, low density
- · Economical printing capability due to white opaque colour
- In line corona treatment is highly recommended

Applications

Designed especially for ice-cream packaging.

PROPERTIES	TEST CONDITIONS		UNITS	TYPICAL VALUES		
THICKNESS			μ	30	33	35
			Gauge	120	140	152
THICKNESS TOLERANCE			%	5		
UNIT WEIGHT	ASTM D 2673		g / m²	18.6 ± 1.1	20.5 ± 1.3	21.7 ± 1.5
YIELD	ASTM D 2673		m² / kg	53.8 ± 4.5	48.9 ± 4.0	46.1 ± 3.5
HAZE	ASTM D 1003		%			
GLOSS	ASTM D 2457		%	> 100		
OPTICAL DENSITY	MACBETH			0.45 ± 0.05	0.50 ± 0.03	0.52 ± 0.03
COEFFICIENT OF FRICTION*	ASTM D 1894	B/B*		< 0.40		
		B/M*		< 0.28		
TENSILE STRENGTH	ASTM D 882	MD	- N/mm²	75 ± 20		
		TD		130 ± 30		
ELONGATION AT BREAK	ASTM D 882	MD	%	140 ± 20		
		TD		38 ± 5		
HEAT SEAL TEMPERATURE	3 Bar / 0.5 Sec		℃	110 - 145		
SEAL STRENGTH	130 ℃ / 3 Bar / 0.5 Sec		N / 15 mm	> 2.0		
WVTR	ASTM F 1249 38 ℃ / 90% RH		g / m² / day	7.0 6.5		6.5
TREATMENT LEVEL	ASTM D 2578		dyne / cm	≥ 36		
HEAT SHRINKAGE	130℃ / 7 mln	MD	%	≤ 5.0		
		TD			≤ 3.0	

 $^{^{\}star}\text{B/B}$: Nontreated side to nontreated side

The above information is the result of laboratory test which are applied on samples from standart production. Since the varying conditions under which our products used are beyond our control, all of the above results are without guarantee and warranty.

POLÍBAK Plastik Film San. ve Tic.A.Ş. AOSB Izmir-TURKIYE Phone: +90 232 3767970 Fax: +90 232 3767730

^{*}All COF values are dynamic results

^{*}B/M: Nontreated side to metal