

Oppalyte™ 30MD447


Oriented Polypropylene Film

Product Description

OPPalyte 30MD447 is a coextruded super white opaque, modified higher density, biaxially oriented polypropylene film, heat sealable on both sides. This opaque and extremely stiff film is ideal for use on VFFS and HFFS machines and is also very well suited for overwrapping applications.

Key Features

- Exceptional stiffness and flex resistance
- Good seal strength
- Excellent dimensional stability
- Good hot slip
- Good hot tack



General

Availability

- ✓ Africa & Middle East
- ✓ Asia Pacific
- ✓ Europe

Features

- ✓ In Lamination Lap Sealable
- ✓ Light Barrier

Applications

- ✓ Biscuits/Cookie/Crackers
- ✓ Confectionery, Sugar
- ✓ Confectionery, Chocolate
- ✓ Household and Detergents
- ✓ Ice Cream
- ✓ Box Overwrap
- ✓ Bakery
- ✓ Frozen Food
- ✓ Crisps and Snacks
- ✓ Confectionery, Gum
- ✓ Fresh Produce
- ✓ Health and Beauty Care
- ✓ Pet Food

Uses

- ✓ Box Overwrap Flexible Packaging
- ✓ Pouches - Flexible Packaging
- ✓ HFFS Flexible Packaging
- ✓ VFFS Flexible Packaging

Appearance

- ✓ White

Processing Method

- ✓ Cold Seal Adhesive
- ✓ Solvent Flexographic Printing
- ✓ Inner Web Extrusion Lamination
- ✓ Inner Web Adhesive Lamination
- ✓ Solvent Rotogravure Printing
- ✓ Outer Web Adhesive Lamination
- ✓ Surface Print Unsupported

Revision date

 October 10, 2013

Properties

Property	Typical Value	Unit	Test Based On
Yield	41.6	m ² /kg	Internal Method
Unit Weight	24.0	g/m ²	Internal Method
Film Thickness	30	μ	Internal Method
Gloss(45°)	55		Internal Method
Light Transmission	33.0	%	Internal Method
Whiteness Index	90		Internal Method
Tensile Strength at Break <i>200 mm/min pull rate, 120 mm jaw separation</i>			
MD	120	Mpa	Internal Method
TD	200	Mpa	Internal Method
Elongation at Break <i>200 mm/min pull rate, 120 mm jaw separation</i>			
MD	160	%	Internal Method
TD	65	%	Internal Method
Dimensional Stability 135°C / 275°F, 7 min			
MD	-3.0	%	Internal Method
TD	-3.0	%	Internal Method
Elastic Modulus			
MD	1700	Mpa	Internal Method
TD	3200	Mpa	Internal Method
Seal Strength (Otto Brügger) <i>140°C, 0.3 Mpa, 2 sec</i>			
	400	g/2.5 cm	Internal Method
Heat Seal Range			
Untreated/Treated	25	°C	Internal Method
Untreated/Untreated	40	°C	Internal Method
Coefficient of Friction			
Untreated Surface	0.25		Internal Method
Treated Surface	0.30		Internal Method
Water Vapor Transmission Rate			
38°C, 90% RH	5.0	g/m ² /24 hr	Internal Method
23°C, 85% RH	1.1	g/m ² /24 hr	Internal Method

Legal Statement

Contact your Jindal Films Customer Service Representative for potential food contact application compliance (e.g. FDA, EU, HPFB). This product is not intended for use in medical applications and should not be used in any such applications.

Processing Statement

- Standard reel winding: Treated side outside

Footnotes

1. Product may not be available in one or more countries in the identified Availability regions. Please contact your Sales Representative for complete country availability.
2. Tested at 38°C (100°F)/100%RH, then calculated to 90%RH with .90 multiplier.

Typical properties: these are not to be construed as specifications.

© 2013 Jindal Films. Jindal Films, the Jindal Films logo, and other product or service names used herein are trademarks of Jindal Films, unless indicated otherwise. This document may not be distributed, displayed, copied or altered without Jindal Films' prior written authorization. To the extent Jindal Films authorizes distributing, displaying and/or copying of this document, the user may do so only if the document is unaltered and complete, including all of its headers, footers, disclaimers and other information. You may not copy this document to, or reproduce it in whole or in part on, a website. Jindal Films does not guarantee the typical (or other) values. Any data included herein is based upon analysis of representative samples and not the actual product shipped. The information in this document relates only to the named product or materials

when not in combination with any other product or materials. We based the information on data believed to be reliable on the date compiled, but we do not represent, warrant, or otherwise guarantee the accuracy, reliability, or completeness of this information; nor do we warrant, expressly or impliedly, the merchantability, fitness for a particular purpose, freedom from patent infringement, or suitability of the products, materials or processes described. The user is solely responsible for all determinations regarding any use of material or product and any process in its territories of interest. We expressly disclaim liability for any loss, damage or injury directly or indirectly suffered or incurred as a result of, or related to, anyone using or relying on any of the information in this document. This document is not an endorsement of any non-Jindal Films' product or process, and we expressly disclaim any contrary implication. The terms "we," "our," "Jindal Films" and "Jindal" are each used for convenience, and may include Films Americas LLC, Jindal Films Americas LLC, Films Europe S.A.R.L. or any companies affiliated with them in the production and sale of film products. There are a number of such affiliated companies, many with names including "Jindal" or "Film". Neither the use of these terms of convenience, nor anything else in this document, is intended to override or supersede the legal separateness of those affiliated companies and responsibility for local action and accountability remains with them.