

shield

shield


MPB

- High-barrier metallized OPP film
- Designed for extrusion lamination



TREOFAN PACKAGING FILM MPB

Metallized co-extruded OPP film with enhanced light, moisture and gas barrier



Treofan MPB is a biaxially oriented, co-extruded polypropylene film. Treofan MPB gives enhanced light and very high moisture and oxygen barrier. With its excellent metal adhesion it allows extrusion as well as adhesive lamination. Its heat-sealable layer on the non-metallized face provides good heat-seal integrity. Reels are normally wound with the metallized face on the outside, but can sometimes be supplied on request with the metallized face wound inside.

PRODUCT FEATURES

Physical characteristics:

- high resistance to tear and puncture
- excellent resistance to low temperatures
- dimensionally stable under conditions of varying humidity
- high heat-seal strength

Film characteristics:

- low water vapour permeability
- water-repellent
- resistance to biological oil and biological grease
- odourless and taste-free
- physiologically harmless, thus suitable for food packaging

Special properties:

- high-barrier properties
- suitable for extrusion lamination

APPLICATIONS AND PROCESSING

Treofan MPB can be used for packaging various types of products, for example products which require higher than standard protection against moisture, odour or dehydration.

Laminating:

- adhesive or extrusion lamination with OPP or with other substrates, depending on application

Packaging:

- Treofan MPB is suitable for use on a variety of form, fill and seal machines

Storage:

- place Treofan MPB in the processing area approximately 24 hours prior to processing

Certified according to

DIN EN ISO 9001:2000

Compliance with industrial health and safety standards: Treofan OPP films do not present any significant danger to health and safety in the workplace, provided they are used for the intended purpose in accordance with conventional practices and that health and safety regulations are observed. Relevant guidelines can be found in our safety information.

TECHNICAL DATA (typical values)

Properties	MPB 17	Unit	Measuring method
Nominal thickness	17	µm	-
Unit weight	15.9	g/m ²	ISO 4591
Density	0.91	g/cm ³	-
Yield	62.9	m ² /kg	-
Heat-seal strength	1.8	N/15 mm	Treofan
Optical density	2.4	-	Tobias densitometer
Tensile strength: machine direction	150	N/mm ²	DIN EN ISO 527-1/-3
transverse direction	270	N/mm ²	DIN EN ISO 527-1/-3
Elongation at break: machine direction	160	%	DIN EN ISO 527-1/-3
transverse direction	60	%	DIN EN ISO 527-1/-3
Water vapour permeability: 38°C/90% rh	0.3	g/m ² ·d ±10 %	ASTM F 1249
Oxygen transmission rates: 23°C/0-90% rh	30	cm ³ /m ² ·d·bar	DIN 53380-3

AVAILABILITY (unprinted film)

Reel length (m):

Packaging film	Standard length	Up to 6-times standard
MPB 17	3,900	23,400

8-times standard or other reel lengths available on request

Maximum reel outside diameter (mm):

Core diameter	Standard length	Up to 6-times standard
77 mm	approx. 330	-
152 mm	approx. 360	approx. 800

Max. reel width: 2,000 mm (widths > 2,000 mm on request)

The figures and the data provided in this data sheet are consistent with the current state of our knowledge, and are intended to provide general information on our products and their applications. They do not constitute a guarantee of any specific product attributes or the suitability of products for specific applications. Any existing commercial rights or patents must be observed.

Tests have shown that under the prescribed storage conditions the characteristics of Treofan MPB will maintain consistent performance and will be best before use throughout a 3-months period after delivery. Treofan MPB is largely unaffected by climatic influences, but should not be stored at temperatures above 30°C (86°F). The rolls should be kept in their original wrapping until used. After the rolls have been unwrapped, they should be stored safely in horizontal position.

Food Safety

Treofan MPB has been developed specially for packaging foods and meets the specific requirements on health and safety. It meets the FDA and EC regulations, which includes the specific "German Food and Commodity Act" and the current recommendations of the BfR. Compliance with other specific national regulations is available on request. It is not recommended that the metalized surface is used in direct contact with food.

HEADOFFICE TREOFAN GROUP

Treofan Germany GmbH & Co. KG
Am Prime Parc 17
65479 Raunheim, Germany
Phone: +49 6142 200 200
Fax: +49 6142 200 3299

SALES CONTACTS

Business Team Head Packaging
Phone: +49 6142 200 3265
Fax: +49 6142 200 3299
guido.bisch@de.treofan.com
Contact: Guido Bisch

Africa
Phone: +27 11 761 7617
gunnar.vahlenkamp@za.treofan.com
Contact: Gunnar Vahlenkamp

Benelux
Phone: +33 5 5660 0994
michel.malet@treofan.com
Contact: Michel Malet

Eastern Europe
Phone: +49 6142 200 3263
peter.breburda@de.treofan.com
Contact: Peter Breburda

Export Treofan Group
Phone: +34 93 306 8327
ignacio.velez@es.treofan.com
Contact: Ignacio Velez

Germany/Switzerland/Austria
Phone: +49 6142 200 3402
urs.ulrich@de.treofan.com
Contact: Urs Ulrich

Iberica
Phone: +34 93 306 8327
ignacio.velez@es.treofan.com
Contact: Ignacio Velez

Italy
Phone: +39 02 6796 3602
sergio.arcari@it.treofan.com
Contact: Sergio Arcari

Mexico/Latin America
Phone: +52 436 363 8044
Phone: +52 436 363 8115
alfonso.flores@mx.treofan.com
Contact: Alfonso Flores

United Kingdom
Phone: +44 1793 34 4004
carey.ashworth@uk.treofan.com
Contact: Carey Ashworth

USA/Canada
Phone: +1 336 766 9448
grant.gustafson@us.treofan.com
Contact: Grant Gustafson



www.treofan.com